

TERMI FLOOR SOIL

CE
EN 13967

WATERPROOF ANTI-TERMITE MEMBRANE FOR FOUNDATIONS

COMPOSITION

- ① single layer: low density PE film



TECHNICAL DATA

Properties	standard	value	USC units
Mass per unit area	-	150 g/m ²	0.49 oz/ft ²
Thickness	-	0,15 mm	6 mil
Tensile strength MD/CD	-	20/19 mPa	2901/2756 psi
Elongation MD/CD	-	550/650 %	-
Resistance to tearing MD/CD	-	3800/5900 g/mm	-
Yield strength MD/CD	-	15/13 Mpa	-
Punching (Dart test)	-	270 g	-
Watertightness (60 kPa)	EN 1928	compliant	-
Reaction to fire	EN 13501-1	class F	-
Resistance to temperature	-	-40/80 °C	-40/176 °F
Density	-	approx. 950 kg/m ³	approx. 59 lbm/ft ³
Action against termites	-	10 years	-

Efficacy testing against ground termites in different geographical areas including Europe, North America, South Africa and Asia. Contact our technical department for further information.

Waste classification (2014/955/EU): 17 02 04.

CODES AND DIMENSIONS

CODE	roll [m]	H [m]	L [m]	A [m ²]	H [ft]	L [ft]	A [ft ²]	
TERMIS150	1,5 x 12,5	6	25	150	20	82	1615	46