



MEMBRANE GLUE

ADHESIVE GLUE FOR SEALING MEMBRANES

EFFECTIVE

Solvent-free acrylic adhesive, with good adherence to the most common supports.

PRACTICAL

Easily extruded mix, ready to use and easily removed with water prior to hardening.



TECHNICAL DATA

Properties	value	USC units
Composition	acrylic without solvents	-
Density ISO 1183	1,05 ± 0,4 g/cm ³	8.76 ± 0.33 lb/gal
Time required for drying 25 °C/50 %RH	24 - 72 hours	-
Resistance to temperature	-20/+80 °C	-4/176 °F
Application temperature (cartridge, ambient and support)	+5/+40 °C	+41/104 °F
Emicode	EC1 plus	-
French VOC classification	A+	-
Transport temperature	0/+35 °C	+32/95 °F
Storage temperature ⁽¹⁾	+10/+25 °C	+50/77 °F

⁽¹⁾ Store the product in a dry, covered location. Check the expiry date on the packaging.

Waste classification (2014/955/EU): 08 04 10.

EUH208 Contains CAS 55965-84-9 (3:1), CAS 2634-33-5. May produce allergic reactions.

CODES AND DIMENSIONS

CODE	content	yield of the glue line Ø8 mm	content	yield of the glue line Ø8 mm	colour	version	
	[ml]	[m]	[US fl oz]	[ft]			
MEMBRAGLUE310	310	6	10.48	20	black	rigid cartridge	24
MEMBRAGLUE600	600	11,6	20.29	38	black	soft cartridge	20



EMICODE EC1 PLUS

Thanks to the special formulation, the glue achieves the highest level of safety with regard to emissions that are harmful to health.

QUICK DRYING

It offers a good compromise between adhesion and fast drying of the outer film, allowing application on vertical surfaces without slipping problems.

RECOMMENDATIONS FOR INSTALLATION: INDOOR GLUES



MEMBRANE CONNECTION TO WALL - CONCRETE



MEMBRANE CONNECTION TO ROOF - CONCRETE



MEMBRANE CONNECTION TO ROOF - OSB





MEMBRANE OVERLAP SEALING



WINDOW HOLE SEALING



1 PLASTER BAND LITE

MEMBRANE CONNECTION TO WALL - CONCRETE



1 PRIMER, PRIMER SPRAY

FLY, FLY SOFT, ROLLER